

GD UPAL DISPLAY TECHNOLOGY CO.,LTD
 NO.53, CHATANG ROAD, CHASHAN TOWN, DONGGUAN CITY, GUANGDONG,CHINA

Sample Description : LINING FABRIC OF TENT

As above test item and its relevant information regarding to the submission are provided and confirmed by the applicant. SGS is not liable to either the test item or its relevant information, in terms of the accuracy, suitability, reliability or/and integrity accordingly.

SGS Ref No. : SDFS2111006987FF
 Sample Receiving Date : Nov 01, 2021
 Test Performing Date : Nov 01, 2021 to Nov 08, 2021
 Test Performed : Selected test(s) as requested by applicant

Test Result Summary

No.	Test(s) Requested	Result(s)	Comments
1	BS 7837-1996 Flammability performance for textiles used in the construction of marquees and similar textile structures	PASS	/
For further details, please refer to the following page(s)			

Signed for and on behalf of
 SGS-CSTC Standards Technical Services Co., Ltd. Shunde Branch



Bill Wang
 Authorized Signatory



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

SGS-CSTC Standards Technical Services Co., Ltd. Shunde Branch Harbin
 1/F, 1st Building, European Industrial Park, No.1 Shunde South Road, Wusha Section, Daliang Town, Shunde, Foshan, Guangdong, China 528333 t (86-757)22805888 f (86-757)22805858 www.sgs.com.cn
 中国·广东·佛山市顺德区大良街道办事处五沙顺和南路1号欧洲工业园一号厂房首层 邮编: 528333 t (86-757)22805888 f (86-757)22805858 e sgs.china@sgs.com

Test Conducted:

The test, specified in BS 7837-1996 flammability performance for textiles used in the construction of marquees and similar textile structures, is based on test 2B of BS 5438:1989.

General Information:

Materials	Fabric	Weight	72.6 g/m ²
Soaking Condition:	YES (Clause 3 in BS 5651)		
Conditioning of Test Specimen(s):	(20±2) °C	RH (65±5) %	24 h
Testing Enclosure (fume cupboard /room):	25.7 °C	RH 62 %	---

Test Criteria:

The sample shall be deemed to perform satisfactorily (pass), if, for at least five of the six test specimens:

- a) The duration of flaming does not exceed 5s after removal of the igniting flame; and
- b) The lowest boundary of any flame does not reach the upper edge or either vertical edge; and
- c) The filter does not smoulder or flame.

The sample shall be deemed not to conform to this British Standard (FAIL) if more than two test specimens show any of the effects listed in items a) to c), if two test specimens show any of the above effects, then a further six specimens shall be tested. In this case, the sample shall be deemed to 'PASS' if five of the second set of six specimens performs satisfactorily.

Test Result:

BS 5438:1989 Test 2B. Bottom edge ignition Flame application time 10s	Test specimen*					
	1	2	3	4	5	6
Duration of flame(s)	0	0	0	0	0	0
Duration of afterglow (s)	0	0	0	0	0	0
Flaming debris(YES or NO)	NO	NO	NO	NO	NO	NO
Flaming to edge (YES or NO)	NO	NO	NO	NO	NO	NO
Hole to edge (YES or NO)	NO	NO	NO	NO	NO	NO
Glow to edge (YES or NO)	NO	NO	NO	NO	NO	NO
Filter Ignition (YES or NO)	NO	NO	NO	NO	NO	NO

*: The tested sample was provided by client with no direction.

Conclusions:

The tested samples PASS the Specification of BS 7837:1996.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

SGS-CSTC Shunde Branch Harbin, Inspection & Testing Services
Shunde Branch Harbin

1/F, Building European Industrial Park, No.1 Shunde South Road, Wusha Section, Daliang Town, Shunde, Foshan, Guangdong, China 528333 t (86-757)22805888 f (86-757)22805858 www.sgs.com.cn
中国·广东·佛山市顺德区大良街道办事处五沙顺和南路1号欧洲工业园一号楼首层 邮编: 528333 t (86-757)22805888 f (86-757)22805858 e sgs.china@sgs.com

Photo Appendix:



End of Report

